


SPIROL Features and Benefits of ArmorGalv[®] Thermal Zinc Diffusion

SPIROL International Corporation



ArmorGalv® Thermal Diffusion 000+ HOURS corrosion resistance

Thermal Diffused Zinc, a finishing process historically known as Sherardizing, has been used for corrosion protection of metal parts for over a century. Over the years, improvements have been made to the Sherardizing zinc/iron diffusion process. The modern, greatly improved process, known as ArmorGalv® is now being introduced as a standard finish for **SPIROL** products, and is poised to revolutionize the market. ArmorGalv[®] is anodic to steel and as such, provides long term sacrificial galvanic protection. Unlike traditional electroplating there is no risk of hydrogen embrittlement, adhesion is superior, coating thickness uniform, and all surfaces are covered. There are no insignificant surfaces. The affordability, durability, and low environmental impact of ArmorGalv[®] makes it ideal for today's market.

ArmorGalv® is a zinc alloy thermal diffusion coating, and is covered by ASTM A1059M-08(2013). This process requires a closed container, heated to a minimum 343°C (650°F), with a powdered zinc mixture. At this temperature sublimation of the zinc mixture occurs and it is dispersed into the container as a vapor. Being soluble in iron, the zinc vapor subsequently diffuses into the surface of ferrous parts. Volume of the zinc mixture is calculated based upon total surface area of the parts resulting in excellent control of resultant thickness with near total consumption of the zinc powder. After the diffusion, specially designed topcoats and sealers are applied to complete the finish. The United States Environmental Protection Agency has stated this finish approaches zero emissions and it has received recognition and awards for its contribution to pollution prevention. There is no hazardous chemistry and water consumption is extremely low. In addition to these benefits, ArmorGalv® exceeds the performance benchmarks of many competing solutions.

SPIROL recommends ArmorGalv® coating as an alternative to traditional platings and coatings for many reasons; chief among them product quality, maximum corrosion protection/ performance, cost effectiveness, and environmental stewardship. Primary benefits of ArmorGalv® are:

1,000 hours or greater corrosion resistance of time to red rust (base metal attack)

ZERO risk of hydrogen embrittlement

Will not reduce fatigue strength of material (applicable to all alloys including stainless)

Uniform deposition of coating on all surfaces (No insignificant surfaces). All internal features or ØID's receive full coating and protection

Cost effective

Anti-galling characteristics similar to cadmium (may be applied to stainless steel)

No flaking, peeling, or blistering - approximately 1/3 of finish thickness is diffused into the coated surface effectively becoming part of the component

Hard and highly abrasion resistant @ 37-42 HRC

Slightly porous surface will retain paint and other coatings in the event complete pinned assembly requires subsequent painting, powder coating, etc.

ArmorGalv[®] offers a low risk, cost effective, high performance alternative to many of today's platings and coatings. With ever-increasing performance and life cycle requirements, this coating is an ideal solution for fasteners used in some of the most aggressive environments such as marine, automotive, mining, and industrial manufacturing. following photographs provide visual representation of this coatings effectiveness.

The image below demonstrates the layered structure of ArmorGalv®. Maximum percentages of zinc occur at the surface with the percent iron increasing with depth (20 microns average coating thickness is applied to SPIROL fasteners):

Uniformity of deposition is visible in the following photographs. Note coverage of all surfaces including peaks, valleys, corners, and gaps:



Fastener and washer with ArmorGalv® coating.

A closer cross-section with thicker deposition for clarity in the two images below:



Powder Metal Parts Before ArmorGalv®

Powder Metal Parts After ArmorGalv® (100 microns / 4mils)

Alpha Layer 92% Iron / 8% Zinc Gamma Layer 50% Iron / 50% Zinc

> Delta Layer 25% Iron / 75% Zinc

Zeta Layer

7% Iron / 93% Zinc

offering. Continuing their 75+ year tradition of innovation in the industry by making the investment in the equipment and tailoring the process to meet the specific needs of their product lines, SPIROL is able to offer this superior coating as an inhouse process at a cost-effective price. As stated by SPIROL's Marketing Manager, Christie Jones, "SPIROL is proud to be a

ArmorGalv® easily exceeds the corrosion requirements of

most industries and is ideally suited for SPIROL's product

part of the ArmorGalv® family. This is most definitely a gamechanger for the fastener industry!"

Contact SPIROL today for more information about ArmorGalv®!

ArmorGalv is RoHS and REACH compliant.

20µm

Base Material



Innovative fastening solutions. Lower assembly costs.



Coiled Spring Pins




Slotted Spring Pins




Solid Pins



Alignment Dowels / **Bushings**



Spacers & Rolled **Tubular Components**



Compression Limiters



Threaded Inserts for Plastics



Railroad Nuts



Disc Springs



Precision Shims & Thin Metal Stampings



Precision Washers



Parts Feeding Technology



Pin Installation Technology



Insert Installation Technology



Compression Limiter Installation Technology

Please refer to www.SPIROL.com for current specifications and standard product offerings.

SPIROL offers complimentary Application Engineering support! We will assist on new designs as well as help resolve issues, and recommend cost savings on existing designs. Let us help by visiting Application Engineering Services on SPIROL.com.

© 2017 SPIROL International Corporation

Technical Centers

Americas

SPIROL International Corporation

30 Rock Avenue

Danielson, Connecticut 06239 U.S.A.

Tel. +1 860 774 8571 Fax. +1 860 774 2048

SPIROL Shim Division

321 Remington Road Stow, Ohio 44224 U.S.A. Tel. +1 330 920 3655 Fax. +1 330 920 3659

SPIROL Canada

3103 St. Etienne Boulevard Windsor, Ontario N8W 5B1 Canada

Tel. +1 519 974 3334 Fax. +1 519 974 6550

SPIROL Mexico

Avenida Avante #250 Parque Industrial Avante Apodaca Apodaca, N.L. 66607 Mexico Tel. +52 81 8385 4390 Fax. +52 81 8385 4391

SPIROL Brazil Rua Mafalda Barnabé Soliane, 134 Comercial Vitória Martini, Distrito Industrial CEP 13347-610, Indaiatuba, SP, Brazil Tel. +55 19 3936 2701

Fax. +55 19 3936 7121

Europe SPIROL United Kingdom

17 Princewood Road Corby, Northants NN17 4ET United Kingdom Tel: +44 (0) 1536 444800 Fax: +44 (0) 1536 203415

SPIROL France

Cité de l'Automobile ZAC Croix Blandin 18 Rue Léna Bernstein 51100 Reims, France Tel: +33 (0) 3 26 36 31 42 Fax: +33 (0) 3 26 09 19 76

SPIROL Germany

Ottostr. 4 80333 Munich, Germany Tel: +49 (0) 89 4 111 905 71 Fax: +49 (0) 89 4 111 905 72

SPIROL Spain

Plantes 3 i 4 Gran Via de Carles III 84 08028, Barcelona, Spain Tel/Fax: +34 932 71 64 28

SPIROL Czech Republic

Evropská 2588 / 33a 160 00 Prague 6-Dejvice Czech Republic Tel: +420 226 218 935

SPIROL Poland

ul. Solec 38 lok. 10 00-394, Warsaw, Poland Tel. +48 510 039 345

Pacific

SPIROL Asia Headquarters

1st Floor, Building 22, Plot D9, District D

No. 122 HeDan Road Wai Gao Qiao Free Trade Zone Shanghai, China 200131 Tel: +86 (0) 21 5046-1451 Fax: +86 (0) 21 5046-1540

SPIROL Korea

16th Floor, 396 Seocho-daero, Seocho-gu, Seoul, 06619, South Korea Tel: +82 (0) 10 9429 1451

e-mail: info@spirol.com

